

Submittal: DWPCW0620W



STRONG-POINT[®] PHILLIPS BUGLE HEAD, COARSE THREAD, WAR COATED

| Size | Part# | Case Qty. | Description |
|-----------|-------|-----------|--|
| 6 x 1-1/4 | 614CW | 8M | Phillips Bugle Head, Coarse Thread, WAR Coated |
| 6 x 1-5/8 | 615CW | 5M | Phillips Bugle Head, Coarse Thread, WAR Coated |
| 6 x 2 | 620CW | 3.5M | Phillips Bugle Head, Coarse Thread, WAR Coated |

Application: Exterior wood screws for outdoor applications.
Attaches wood to wood.

Specifications:

- Meets ASTM¹ A 510 for carbon steel manufacturing
- Product meets ASTM B-117 for salt spray corrosion testing

Features:

- WAR coating exceeds 1,000/hr. salt spray resistance
- Designed to work with ACQ treated lumber



Coating: The WAR coating is a high-grade metal surface processing technology that prevents corrosion. The system consists of three layers: a metallic zinc layer, a hex-chromium or trivalent chromate passivation, and a high-grade anti-corrosion chemical conversion film.

Installation: A standard screw gun with torque limiting nose piece set at a maximum of 3000 RPM drive speed recommended. Use a #2 reduced Phillips drive bit. The fastener is completely installed when the fastener head is seated flush with the work surface. Do not over torque as it can cause the head to snap or damage to the work surface.

¹(American Society of Testing Materials)